



TIKKURILA

Fontecryl SC 50

A water-borne acrylic paint

Fontecryl SC 50 is a one-component alkyd-modified acrylic paint, which contains active anticorrosive pigments. It is characteristic for Fontecryl SC 50 that it forms a harder and more durable paint film than conventional acrylate paints. It is also possible to apply thick films.

This single-coat product also dries very fast, and therefore the packing of painted objects is possible shortly after painting. This will increase the productivity of the application line. Furthermore, the product has a very low VOC content.

Fontecryl SC 50 is suitable for product painting in the metal industry and painting stations. Typical uses are machinery and equipment and steel frameworks. As it has high sagging value Fontecryl SC 50 is also suitable for painting multiform objects.

- fast drying -packing is possible shortly after painting
- easy to apply
- excellent spraying properties
- a single-coat paint
- suitable also for repair and maintenance painting
- depending on film thickness, fulfills the requirements for corrosivity categories C2-C3
- cost effective



FONTECRYL SC 50

A water-borne acrylic paint

A COMPETITIVE EDGE WITH COLOURS

The **significance of** colour design and colour marketing in the manufacture of industrial products is increasing. Colours make products unique and help them stand out. Colours also highlight products' shape and structure. Fontecryl SC 50 has base paints and can thus be tinted in exactly the colour shades that best differentiate your products from the competing ones.

PAINT SYSTEM FOR FONTECRYL SC 50

Product	Dry film thickness	Corrosivity category
Fontecryl SC 50	1 x 80µm	C2-H

FOR PROFESSIONAL RESULTS SPECIFY TIKKURILA

Additional information is available from product data sheet and material safety data sheet. Our experienced staff will be pleased to provide full information on coatings specifications and test reports. Contact your nearest Tikkurila technical center.

Technical information

Volume solid	40%
VOC content in ready-to-use paint	35 g/l
Gloss	Semi-gloss
Colours	Temaspeed Fonte tinting
Drying properties, touch dry	3 h / 15°C 1½ h / 23°C 15 min / 60°C

